



220002349162



中国认可
国际互认
检测
TESTING
CNAS L0690

TEST REPORT

Report No.: WT2024B01B00231EG1

Entrusted by:

Yaret Industrial Group Co.,Ltd

Sample Name:

Aluminum panels※

Test Type:

Entrustment test

China Testing & Certification International Group Co.,Ltd.
National Research Center of Testing Techniques for
Building Materials



WT2024B01B00231



Test Report

Report No.: **WT2024B01B00231EG1**

Page 1 of 3

Sample(s) Name	Aluminum panel※	Test Type	Entrustment test
Client	Yaret Industrial Group Co.,LTD	Brand	YARET
Manufacture	Jiangsu Yaret Technology Industrial Park Co.,LTD	Sample State	Meet the requirements of testing
Receiving Date	February 27, 2024	Quantity of sample(s)	300mm×300mm 12 Pcs. 75mm×150mm 15 Pcs. 100mm×430mm 3 Pcs.
Production Date	January 2, 2024 /20240102	Model/Size	Plate thickness 3mm Outdoor dual coating of FC liquid spraying system※
Test Method(s)	The method for the test items are detailed in the data page(s).	Test Date	February 28th to March 5th, 2024
Judgment Standard(s)	GB/T 23443-2009 Aluminum panels for building decoration		
Test Item(s)	Test items are detailed in data pages.		
Test Result(s)	<p>* Upon testing, the test result of gloss tolerance is shown in page 2, other tested results comply with the requirements of GB/T 23443-2009 for outdoor dual coating of FC liquid spraying system, Test result are detailed in data pages.*</p> <p style="text-align: right;">Date of issue: 2024-07-19 (Seal)</p>		
<p>Remarks: 1. This report is a modification of the testing report with the serial number WT2024B01B00231 issued on March 8, 2024. The change is marked with the symbol ※, and the original report is invalid from today onwards; (Provided by the commissioning unit)2. Sample number: YT-002; 3、YARET brand.</p>			

Approved by

Checked by

Compiled by

Address: No.1 Guanzhuang Dongli ,Chaoyang District, Beijing, China
Tel: 00-86-10-51167681

P.C.: 100024

China Testing & Certification International Group Co.,Ltd.
National Research Center of Testing Techniques for Building Materials
Test Report

Report No.: WT2024B01B00231EG1

Page 2 of 3

No.	Test Item(s)	Requirements of Standard(s)	Test Result(s)	Individual Conclusion	Test method(s)	
1	Coating thickness	Avg. $\geq 30\mu\text{m}$	31 μm	Pass	GB/T 23443-2009 7.4 GB/T 4957-2003	
		Min. $\geq 25\mu\text{m}$	29 μm	Pass		
2	Gloss tolerance	Gloss value < 30	Gloss range 21.1~24.9 Avg. 23.1	—	GB/T 23443-2009 7.5 GB/T 9754-2007	
		$30 \leq$ Gloss value < 70				Tolerance ± 7
		Gloss value ≥ 70				Tolerance ± 10
3	Film adhesion	Dry adhesion	Cross-cut Rating 0	Pass	GB/T 23443-2009 7.6.1 GB/T 9286-2021	
		Wet adhesion	Cross-cut Rating 0	Pass	GB/T 23443-2009 7.6.2 GB/T 9286-2021	
		Boiling water adhesion	Cross-cut Rating 0	Pass	GB/T 23443-2009 7.6.3 GB/T 9286-2021	
4	Pencil hardness	$\geq 1\text{H}$	2H (CHUNG HWA Pencil)	Pass	GB/T 23443-2009 7.7 GB/T 6739-2022	
5	Hydrochloric acid resistance (5%HCl (V/V),24h)	Unchanged	Unchanged	Pass	GB/T 23443-2009 7.8.1.1	
6	Nitric acid resistance	No blistering and no other changes. $\Delta E \leq 5.0$	No blistering and no other changes. $\Delta E = 0.25$	Pass	GB/T 23443-2009 7.8.1.2	

China Testing & Certification International Group Co.,Ltd.
National Research Center of Testing Techniques for Building Materials
Test Report

Report No.: WT2024B01B00231EG1

Page 3 of 3

No.	Test Item(s)	Requirements of Standard(s)	Test Result(s)	Individual Conclusion	Test method(s)
7	Mortar resistance	Unchanged	Unchanged	Pass	GB/T 23443-2009 7.8.2
8	Solvent resistance	Bottom leakage prevention	Bottom leakage prevention	Pass	GB/T 23443-2009 7.8.3
9	Abrasion resistance	$\geq 5L/\mu m$	7.2L/ μm	Pass	GB/T 23443-2009 7.10 Annex B
10	Impact resistance	No cracking on both sides of aluminum sheet, no cracking and removal of coating from substrate	No cracking on both sides of aluminum sheet, no cracking and removal of coating from substrate	Pass	GB/T 23443-2009 7.11 GB/T 1732-2020

(Blank)

Annotations: Test address: No.1, Guanzhuang Dongli, Chaoyang District, Beijing, China/100024.

————— **End of the Report** —————

Address: No.1 Guanzhuang Dongli, Chaoyang District, Beijing, China
 Tel: 00-86-10-51167681

P.C.: 100024